



Timbakote Ltd
15 Pahoia Beach Rd
Tauranga
12 August 2006

Hi Brian,

We have completed the elongation and tensile strength testing that you requested.

The results are:

Timbakote Natural Timber Finish

Tensile strength at break 7.62N/10mm
Elongation at break 480%

Competitive Product

Tensile 4.68 N/10mm
Elongation 450%

Acrylic Exterior Paint

Tensile 10.02 N/10mm
Elongation 105%

Tensile strength; N is Newton, the basic metric unit used for Strength. It is defined as "imparting acceleration of 1metre / second / second to 1 kg mass" Timbakote is approx 60% stronger then its competitive product.

Elongation; Timbakote stretches slightly further than the competitive product before the film fractures.

ESP COMPANY LTD
P O BOX 78 189
GREY LYNN
AUCKLAND 1245
Ph09 3789174
Mob 027 4771833
espco@wave.co.nz

Kevin Purdy

Timbakote Limited, 15 Pahoia Beach Road, Tauranga. 3172. Phone: 07 5480 631.
Fax: 07 5480 181. Email: info@timbakote.co.nz. Website: www.timbakote.co.nz