



Timbakote Natural Timber Finishes Light Reflectance Values

Timbakote Name	Ill/Obs	LRV
Birch Grey	D65/10	44
Black Bean	D65/10	31
Capers	D65/10	54
Cedar	D65/10	43
Charcoal	D65/10	33
Chestnut	D65/10	33
Dark Oak	D65/10	34
Dusk	D65/10	67
Ebony	D65/10	36
Eucalyptus	D65/10	50
Iron Bark	D65/10	55
Karaka	D65/10	43
Kelp	D65/10	40
Light Cedar	D65/10	57
Light Grey	D65/10	55
Light Oak	D65/10	56
Mahogany	D65/10	30
Manuka Honey	D65/10	64
Nutmeg	D65/10	52
Redwood	D65/10	39
Sapling	D65/10	55
Slate	D65/10	56
Smokey Ash	D65/10	65
Teak	D65/10	41

Light Reflectance Values testing was done on Leneta Opacity Card 2c over 89 LRV background. Draw down at 90 microns wet film build.

NB; Light Reflectance Values for semi-transparent coatings will vary with different substrates & different film build applications. The above is a guide only.